ROLIGHT Lightbox Products

Monomeric Lightbox Vinyl Lightbox Films SVBL-R



ROCAL Monomeric vinyls have been engineered for a large range of wide format digitally printed & mounted graphic applications using face stock weights & formulations that consistently capture and display ink effectively whilst providing mid term durability & excellent resistance to shrinkage. SVBL-R is a satin translucent film with a removable, solvent based acrylic adhesive which can be wet applied and later removed without leaving residue. It has a two side coated, moisture resistant, stayflat paper liner.



Performance

Premium



Composition: Calandered PVC film, adhesive & release paper

Main Applications: Removable printed graphics mounted to light box substrates Features: Controlled, reliable print formulation & shrinkage, stay-flat liner Benefits: Reliable printing, high durability & flatness, visually appealing &

removable

Formulation: Monomeric Vinyl Storage Conditions: 5~40°C & 35~75% RH

Shelf Life: 1 year from date of manufacture Release Liner: 0.18mm, 120gsm double PE coated Adhesive Type: Removable solvent based acrylic

Remarks: Total weight including liner & adhesive 320gsm



Quality & Testing

• Durability ISO 4892-3 (1000hr)

Application

 Short term light box graphics

Manufacturing

ISO9001



• 320 grams per m² ± 5%

Stock Availability

Sheet Sizes: See sheet cutting Roll Widths (mm): 1370 & 1524

Roll Lengths (mtrs): 50

Log Cutting: Up to 1524mm Standard Core: 76mm ID

Sheet Cutting: Up to 3200mm x 1524mm





6 years



3 years



Safety Compliance RoHs Certified

Printing

Method: UV Offset, Screen & Digital Printable Sides: One, wound facing outside of roll

Ink Suitability: UV Cured inks (Offset, Screen & Inkjet), Latex & Solvent

Basic Physical Data

Thickness: 305 micron

Weight: 320 grams per m² ± 5%

Gloss Level: Satin

Thermal Data

Heat Resistance: 80°C Cold Resistance: -30°C

Shrinkage: 0.5 ↓ % (80°Cx48hrs)





ROLIGHT Lightbox Products

Monomeric Lightbox Vinyl Lightbox Films SVBL-R



Physical Characteristics

Holding Power 0.3 ↓ mm (JIS Z 0237) **Ball Tack** 5 ~ 10 (JIS Z 0237)

1800 Peel 1800 ↑ g/25mm-24Hr (JIS Z 0237)

Adhesion

90° Release 40±20 g/50mm (JIS Z 0237)

Force

Thickness Film 100micron, Liner 180micron,

Adhesive 25micron

Weight 320 grams per m² \pm 5% Tensile 2000 \uparrow g/10mm (JIS Z 0237)

Strength

Elongation at 150 ↑% (JIS Z 0237)

Break

Gloss Level 80↑ Degree/60°Angle (ISO 2813)

Surface Finish Satin

UV Stabilized Yes, to maximum concentration

\
lFinishind
,

Cutting	\checkmark
Welding	X
Folding	\checkmark
Gluing	\checkmark
Eyeletting	\checkmark
Stitching	X
Laminating	\checkmark
Bending	\checkmark
Routing	X
Punching	\checkmark
Drilling	\checkmark
Screwing	\checkmark
V-Grooving	X